

# KIRTON CONCRETE SERVICES LTD

INDEPENDENT TESTING LABORATORY

Manor House, Station Road, Hibaldstow, Brigg, North Lincolnshire, DN20 9EB, England

Telephone: (01652) 656931 : Fax: (01652) 651082 : E-mail Kirtonlab@aol.com



1175

## CEMENT TEST RESULTS

Client :- TITAN CEMENT LTD., HULL  
Report Reference :- TITAN 6049  
Week reference :- TITAN 48 2015  
Sample :- ORDINARY PORTLAND CEMENT  
Sand :- FRENCH  
Date of receipt of sample :- 08/12/2015  
Date of tests :- 08/12/2015 to 05/01/2016  
Date of Report :- 06/01/2016

### RESULTS

FINENESS 3880 cm<sup>2</sup>/g (BS EN196 PART 6:2010 )  
STANDARD CONSISTENCE 28.0 % (BS EN196 PART 3:2005)  
INITIAL SETTING TIME 175 mins (EN196 PART 3:2005)

### COMPRESSIVE STRENGTH :- MORTAR PRISMS

(EN196 PART 1:2005)

AT 2 DAYS 31.2 MPa (Mean of 6 results, none discarded)  
AT 7 DAYS 49.9 MPa (Mean of 6 results, none discarded)  
AT 28 DAYS 59.8 MPa (Mean of 6 results, none discarded)

### CHEMICAL COMPOSITION :- by mass, as received


Chloride 0.01 % ( EN196 PART2:2013)  
Average Chloride 0.02 last 25 Results  
Na<sub>2</sub>O 0.14 % ( EN196 PART2:2013)  
K<sub>2</sub>O 0.52 % ( EN196 PART2:2013)  
Na<sub>2</sub>O (equiv) 0.48 % ( EN196 PART2:2013)  
Na<sub>2</sub>O Average Alkalis 0.52 last 25 Results EN197-1:2000 N.B.4.3

End of Report

THE ABOVE RESULTS COMPLY WITH THE REQUIREMENTS OF  
BS EN 197-1:2011 FOR CEM 1 52.5 N

Signed

Certificate signed by:  
S.Burton A.M.I.C.T  
Technical Manager



J.M. Burton  
Quality Manager

06/01/2016

Page 1 of 1